

## Aluma-Foil FOIL / LINER / FOIL

FACING COMPOSITION	DESCRIPTION	VALUES (ENGLISH)	VALUES (METRIC)
Foil	Aluminum	0.0003 inch	7.6 micron
Adhesive	Emulsion		
Kraft Liner	Natural	38 lbs / 1000 ft <sup>2</sup>	186 gm / m <sup>2</sup>
Adhesive	Emulsion		
Foil	Aluminum	0.0003 inch	7.6 micron

PHYSICAL PROPERTIES	TEST METHOD	VALUES (ENGLISH)	VALUES (METRIC)
Basis Weight	Scale	48 lbs / 1000 ft <sup>2</sup>	235 gm / m <sup>2</sup>
Permeance (WVTR)	ASTM E96 Procedure A	0.02 perm (grains/hrft <sup>2</sup> in Hg)	1.15 ng / Ns
Bursting Strength	ASTM D774	90 psi	6.3 kg / cm <sup>2</sup>
Puncture Resistance	ASTM C1136	40 beach units	1.2 Joules
Tensile Strength	ASTM C1136	85 lbs/inch width (MD) 35 lbs/inch width (XD)	14.9 kn / m (MD) 6.1 kn / m (XD)
Caliper / Thickness	Micrometer	0.012 inch	305 micron
Accelerated Aging	30 Days @ 95% RH, 120°F (49°C)	No Corrosion No Delamination	No Corrosion No Delamination
Low Temperature Resistance	ASTM D1790 -40°F (-40°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
High Temperature Resistance	4 hours @ 240°F (116°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
Water Immersion	24 hours @ 73°F (23°C)	No Delamination	No Delamination
Mold Resistance	ASTM C665	No Growth	No Growth
Dimensional Stability	ASTM D1204	0.25%	0.25%
Emissivity	ASTM E408	0.03	0.03

FIRE TESTING		
	E-84	
	Flame Spread	Smoke Developed
Foil Exposed	3	3

Physical Properties based upon statistical averages, Weight / Thickness +/- 10%

**“LAMTEC” AND “WMP” ARE REGISTERED TRADEMARKS OF LAMTEC CORPORATION**

Advanced Foil Systems      820 South Rockefeller Avenue      Suite A      Ontario, California 91761  
(909) 390-5125      Fax: (909) 390-5127