

WMP-10 BLACK

BLACK COATING / POLYPROPYLENE / SCRIM / KRAFT

Meets ASTM C1136, Type II, IV

| FACING COMPOSITION | DESCRIPTION | VALUES (ENGLISH) | VALUES (METRIC) |
|--------------------|--------------------------|-------------------------------|------------------------|
| Black Coating | Flame Resistant | 0.0002 inch | 5.1 micron |
| Film | Metallized Polypropylene | 0.0015 inch | 38.1 micron |
| Adhesive | Flame Resistant | | |
| Reinforcing | Tri-directional | 5 / inch (MD) | 20 / 100 mm (MD) |
| | Fiberglass/Polyester | 5 / inch (XD) | 20 / 100 mm (XD) |
| Kraft | White | 14 lbs / 3000 ft ² | 23 gm / m ² |

| PHYSICAL PROPERTIES | TEST METHOD | VALUES (ENGLISH) | VALUES (METRIC) |
|-----------------------------|-----------------------------------|--|-------------------------------------|
| Basis Weight | Scale | 21 lbs / 1000 ft ² | 103 gm / m ² |
| Permeance (WVTR) | ASTM E96 Procedure A | 0.02 perm (grains/hrft ² in Hg) | 1.15 ng / Ns |
| Bursting Strength | ASTM D774 | 65 psi | 4.6 kg / cm ² |
| Puncture Resistance | ASTM C1136 | 125 beach units | 3.7 Joules |
| Tensile Strength | ASTM C1136 | 40 lbs/inch width (MD) 35 lbs/inch width (XD) | 7.0 kn / m (MD) 6.1 kn / m (XD) |
| Caliper / Thickness | Micrometer | 0.009 inch | 229 micron |
| Accelerated Aging | 30 Days @ 95% RH, 120°F (49°C) | No Corrosion No Delamination | No Corrosion No Delamination |
| Low Temperature Resistance | ASTM D1790 -40°F (-40°C) | Remains Flexible No Delamination | Remains Flexible No Delamination |
| High Temperature Resistance | 4 hours @ 240°F (116°C) | Remains Flexible No Delamination | Remains Flexible No Delamination |
| Water Immersion | 24 hours @ 73°F (23°C) | No Delamination | No Delamination |
| Mold Resistance | ASTM C665 / C1338 | No Growth | No Growth |
| Dimensional Stability | ASTM D1204 | 0.25% | 0.25% |

| FIRE TESTING | UL-723 / ASTM E84 | |
|---------------|-------------------|-----------------|
| | Flame Spread | Smoke Developed |
| Film Exposed | 10 | 10 |
| Kraft Exposed | 15 | 5 |

Physical Properties based upon statistical averages, Weight / Thickness +/- 10%

“LAMTEC” AND “WMP” ARE REGISTERED TRADEMARKS OF LAMTEC CORPORATION

Advanced Foil Systems 820 South Rockefeller Avenue Suite A Ontario, California 91761
(909) 390-5125 Fax: (909) 390-5127